

## CHEPSTOW

## PRODUCT INFORMATION



Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

## TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	T1, R1
Configuration	Perforated
Voids	≤ 37%
Mean Compressive Strength	35 N/mm <sup>2</sup>
Active Soluble Salts	S2
Water Absorption	≤ 8%
Durability	F2
Gross Dry Density	1400 Kg/m <sup>3</sup>
Equivalent Thermal Conductivity	0,35 W/ mK
Initial Rate of Absorption	≤ 0,5 Kg/(m <sup>2</sup> ·min)

Issue Date: June 2022